

Table 3. Flotation Test Results – Samples from individual drill holes.

Test Number	6719-8	6719-9	6719-10	6719-11	6719-12
Sample ID	R83	R18	R18	R41	R18
Depth (meters)	0.00 – 5.94	5.33-10.36	0.0-10.36	0.00 – 5.94	0.0 -5.33
	<i>Feldspar Tailings Cum. % Retained</i>				
US 40 mesh	30.7	28.1	33.2	39.4	37.8
US 60 mesh	60.7	57.3	62.1	68.1	66.2
US 100 mesh	86.4	85.5	88.2	91.0	90.9
US 140 mesh	93.3	93.5	94.6	96.3	96.3
Float Yield, Wt.% (Note 1)	80.1	81.0	78.0	74.9	75.5
Final Non-magnetic Yield, Wt. % (Note 2)	78.3	78.9	76.7	73.8	74.1

Note 1 - The yield of sand after removal of mica, iron minerals and feldspar.

Note 2 - The yield after magnetic separation of the sized feldspar tailings.